

## 2A High Precision Tweezers



4 3/4" 120 mm

Flat accurate round tips

2A.SA

**Anti-Magnetic Anti-Acid Stainless Steel**

### General Notes

- low carbon austenitic steel (Material number 1.4435, DIN X2CrNiMo18-14-3, AISI number 316L)
- contains from 16.5 to 18.5 wt% chromium and has important quantities of nickel and molybdenum as additional alloying elements
- non-magnetizable
- good corrosion resistance to most chemicals, salts and acids
- generally used where corrosion resistance and toughness are primary requirements
- typical applications include tweezers for the electronic industry, watch-makers, jewelers and laboratory and medical applications in moderately aggressive chemical environments

### Composition

| Component | Wt. % | Component | Wt. % | Component | Wt. % |
|-----------|-------|-----------|-------|-----------|-------|
|-----------|-------|-----------|-------|-----------|-------|

|    |         |    |           |    |           |
|----|---------|----|-----------|----|-----------|
| C  | ≤0.03   | Si | ≤1.0      | Mn | ≤2.0      |
| P  | ≤0.045  | S  | ≤0.03     | Cr | 17.0-19.0 |
| Mo | 2.5-3.0 | Ni | 12.5-15.0 |    |           |

## Mechanical properties:

|                            |                       |
|----------------------------|-----------------------|
| State                      | annealed              |
| Density                    | 8.0 g/cm <sup>3</sup> |
| hardness HB30              | ≤215                  |
| Hardness Rockwell B        | 79                    |
| Tensile strength, ultimate | 500-700 MPa           |
| Tensile strength, yield    | 290                   |
| 0.2% Yield stress          | ≤200 MPa              |
| Elongation, break          | 40%                   |
| Modulus of elasticity      | 200 GPa               |

## Thermal properties

|                               |              |            |
|-------------------------------|--------------|------------|
| Coef. of lin. therm expansion | 16.0 E-6/°C  | 20°C-100°C |
| Coef. of lin. therm expansion | 17.0 E-6/°C  | 20°C-300°C |
| Specific heat capacity:       | 0.50 J/(g·K) |            |
| Thermal conductivity:         | 15W/(m·K)    |            |
| Continuous use temperature:   | 350°C        |            |
| Max service temperature, ait  | 925°C        |            |

## Electrical properties

|             |                 |
|-------------|-----------------|
| Resistivity | 0.75 E-4 Ohm.cm |
|-------------|-----------------|

© IDEAL-TEK SA

Credits